

## LIDDING FILMS



### TECHNICAL SUPPORT

We pride ourselves in providing high quality services and technical support to all customers.

### CONTACT INFORMATION

For more information on any of our products or services, please contact us at:

Golden Eagle Extrusions, Inc.  
1762 State Route 131  
Milford, Ohio 45150  
P - 800.634.3355  
F - 513.248.8300

[www.goldeneagleextrusions.com](http://www.goldeneagleextrusions.com)  
[info@goldeneagleextrusions.com](mailto:info@goldeneagleextrusions.com)

# EPL-200W

## STANDARD THICKNESS - 2.0 MIL

**EPL-200W** is a white, medium barrier, peelable lidding film. This IMS certified film gives excellent seal peel performance to APET, CPET, PVC, PP, PS, aluminum and paper-board containers.

### Key Features

- Medium moisture and oxygen barrier
- Superior machinability
- Great as lidding material for fresh or frozen foods
- Optimal sealing temperature of 375° F

PROPERTIES	UNIT	TESTING METHOD	TYPICAL VALUES
<b>MECHANICAL</b>			
Tensile Strength MD TD	lb/in <sup>2</sup>	ASTM D882	9,000 9,500
Elongation MD TD	%	ASTM D882	100 100
<b>PHYSICAL</b>			
Yield	in <sup>2</sup> /lb		12,500
COF Sealant side Heat resistant side		ASTM D1894	<.40 0.5
Haze	%	ASTM D1003	28
<b>BARRIER</b>			
MVTR	g/100 in <sup>2</sup> /day	ASTM F1249 38°C, 100%RH	0.5
OTR	cc/100 in <sup>2</sup> /day	ASTM D3985 23°C, 0%RH	6
<b>THERMAL</b>			
Vicat Softening Temperature	F	ASTM D1525	220°

**Disclaimer:** Nothing in this data sheet is to be taken as a warranty. Offered for your consideration only, the information provided herein represents our best knowledge and judgment. Golden Eagle Extrusions, Inc. assumes no liability whatsoever in connection with the use of this information.