


LAMINATION FILMS



TECHNICAL SUPPORT

We pride ourselves in providing high quality services and technical support to all customers.

CONTACT INFORMATION

For more information on any of our products or services, please contact us at:

Golden Eagle Extrusions, Inc.
1762 State Route 131
Milford, Ohio 45150
P - 800.634.3355
F - 513.248.8300

www.goldeneagleextrusions.com
info@goldeneagleextrusions.com

PL-250

STANDARD THICKNESS - 2.5 MIL

PL-250 is a medium barrier, peelable lidding film. This lidding film gives excellent seal peel performance to APET, CPET, PVC, PP, PS, aluminum and paperboard containers.

Key Features

- Medium moisture and oxygen barrier
- Strong, durable film
- Superior machinability
- Great as lidding material for fresh or frozen foods
- Optimal sealing temperature of 375° F

| PROPERTIES | UNIT | TESTING METHOD | TYPICAL VALUES |
|---|-----------------------------|----------------------------|----------------|
| MECHANICAL | | | |
| Tensile Strength MD TD | lb/in ² | ASTM D882 | 8,700 9,200 |
| Elongation MD TD | % | ASTM D882 | 110 110 |
| PHYSICAL | | | |
| Yield | in ² /lb | | 10,600 |
| COF Sealant side Heat resistant side | | ASTM D1894 | <.40 0.5 |
| Haze | % | ASTM D1003 | 28 |
| BARRIER | | | |
| MVTR | g/100 in ² /day | ASTM F1249 38°C, 100%RH | 0.5 |
| OTR | cc/100 in ² /day | ASTM D3985 23°C, 0%RH | 6 |
| THERMAL | | | |
| Vicat Softening Temperature | F | ASTM D1525 | 220° |

Disclaimer: Nothing in this data sheet is to be taken as a warranty. Offered for your consideration only, the information provided herein represents our best knowledge and judgment. Golden Eagle Extrusions, Inc. assumes no liability whatsoever in connection with the use of this information.